



# NITRILE/PVC BLEND RUBBER

TYPE	RATIO NBR/PVC*	NOMINAL ACRYLONITRILE CONTENT WT. %	POLIMERIZATION TEMPERATURE	NOMINAL MOONEY VISCOSITY ML 1 + 4 (100°C)	SPECIFIC GRAVITY	PRODUCT STAIN
UNIMIC 7028	70/30	28	COLD	75 ± 5	1,07	NST
UNIMIC 7033	70/30	33	COLD	75 ± 5	1,08	NST
UNIMIC 7039	70/30	39	COLD	75 ± 5	1,1	NST
UNIMIC 7045	70/30	45	COLD	90 ± 5	1,12	NST
UNIMIC 5033	50/50	33	COLD	65 ± 5	1,13	NST

\* ACCORDING TO THE CUSTOMER'S DEMANDS WE CAN MODIFY THE NBR/PVC RATIO.